



Cement Prehydration Report

Revision 2.1

Date submitted: 05/05/2017

Company contact: John Doe

Email address: john.doe@cement.com

Company name: Cement Company

Input Data

LOI (25°C-70°C)	0.08	%
LOI (70°C-140°C)	0.55	%
LOI (140°C-450°C)	0.97	%

The free moisture in the cement is acceptable, and no build-ups is expected in the storage silos. The theoretical impacts of prehydration on your cement performance is as follows:

MPa loss	2D	7D	28D
	4	4	4